

Product : **Silicon Metal**

Trade name : **SIMET HQ**

References : **SM. 04/14**

CHEMICAL/PHYSICAL ANALYSIS	SIMET 993	SIMET 996	SIMET 999
Si	99,3% min.	99,6% min.	99,9% min.
Fe	0,20% max.	0,05% max.	PPM 70 max.
Al	0,25% max.	0,08% max.	PPM 50 max.
Ca	0,04% max.	0,015% max.	PPM 60 max.
C	0,15% max.	0,15% max.	PPM 25 max.

STANDARD SIZE

We process in all sizes requested by customers from 2 microns to any other coarser grade.

LABORATORY

1/03/2014

APPLICATION

- Desoxydation for refractory
- Production of silicone
- Alloying in aluminium
- Pyrotechnic (Delay Charges)
- Breaks applications

All figures are given for information only. These have to be reconfirmed with our offer.